



VJRICE

CONCRETE LIMITED

Specialist in concrete products.

Phone (902) 665-4444

Fax (902) 665-4017

P.O. Box 399, Bridgetown

Nova Scotia, B0S 1C0

VALLEY STONE BRICK, BLOCK & TUMBLED STONE

- 1. To meet specified requirements of CSA Standard A165.2 (latest standard).**
- 2. Minimum compressive strength: 30 MPa**
- 3. Aggregate shall conform to the requirements of CSA Standard CAN 3A23.1-(latest standard) with the following further qualifications:- to provide required architectural appearance, aggregate shall be granodiorite containing between 10% and 20% quartz, light coloured feldspars, and less than 15% mafic particles.**
- 4. Maximum water absorption: 6% for 24 hour absorption test. Average for 5 units with a maximum 7.5% for any one unit.**
- 5. The units containing the proposed aggregate shall have an acceptable service record of at least 20 years.**